

PATENT
Attorney Docket No. 037768-0173
Application No. 10/698,564

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently amended) A method of manufacturing powder comprising:

providing a metal-containing precursor;

feeding the metal-containing precursor to a reaction zone thereby creating a vapor of the precursor;

adding a reactive fluid to the metal-containing precursor in the reaction zone thereby creating a stream comprising reacted vaporized metal-containing precursor and reactive fluid, wherein the metal-containing precursor is selected from the group consisting of metal acetates, metal carboxylates, metal nitrates, metal sulfates, and metal hydroxides;

~~conducting high temperature processing of the stream comprising reacted metal-containing precursor at temperatures greater than 2500~~ a temperature ranging from 1500 to 4000°C to create a vapor;

cooling the vapor to form a vapor stream comprising nucleated nanoscale powders;

quenching the vapor stream comprising nucleated nanoscale powders thereby preventing agglomeration and ~~grain growth;~~ growth.

~~harvesting the nucleated nanoscale powders.~~
2. (Withdrawn) The method of claim 1, wherein the metal-containing precursor is selected from the group comprising an emulsion, fluid, particle-containing liquid slurry, a gas, a solid, a single-phase liquid, a multi-phase liquid, a melt and a fluid mixture.
3. (Canceled).
4. (Currently amended) The method of claim 1, wherein the metal-containing precursor comprises a mixture of multiple metals metal-containing precursors.

PATENT

Attorney Docket No. 037768-0173

Application No. 10/698,564

5. (Withdrawn) The method of claim 1, wherein the nanoscale powder comprises a metal.
6. (Withdrawn) The method of claim 1, wherein the reactive fluid comprises oxygen.
7. (Withdrawn) The method of claim 1, wherein the reactive fluid comprises carbon.
8. (Withdrawn) The method of claim 1, wherein the reactive fluid comprises nitrogen.
9. (Withdrawn) The method of claim 1, wherein the reactive fluid comprises boron.
10. (Withdrawn) The method of claim 1, wherein the reactive fluid comprises hydrogen.
11. (Currently amended) The method of claim 1, wherein the ~~step of~~ feeding the metal-containing precursor to the reaction zone comprises of spraying that enhances heat transfer efficiency, mass transfer efficiency, momentum transfer efficiency, and reaction efficiency.
12. (Original) The method of claim 1, wherein the reaction zone is surrounded by a concentric zone to reduce non-uniformities in heat, mass or momentum transfer.
13. (Currently amended) The method of claim 1, wherein the ~~step of~~ conducting high temperature of the stream processing is achieved using one or more of the ~~means~~ techniques selected from the group consisting of plasma processes, internal energy, heat of reaction, conduction, convection, radiation, inductive, microwave, electromagnetic, direct electric arc, pulsed electric arc, laser and nuclear.
14. (Original) The method of claim 1, wherein the reacted metal-containing precursor is product of combustion.
15. (Currently amended) The method of claim 1, wherein the ~~step of~~ conducting high temperature processing is performed at temperatures greater than 3000 °C.
16. (Currently amended) The method of claim 1 further comprising ~~a step wherein~~ adding carrier particles ~~are added~~ to a later stage of the high temperature processing.
17. (Currently amended) The method of claim 1, wherein the harvesting is accomplished using one or more ~~means~~ techniques selected from the group consisting of bag filtration, electrostatic separation, membrane filtration, cyclones, impact filtration, centrifugation,

PATENT

Attorney Docket No. 037768-0173

Application No. 10/698,564

hydrocyclones, thermophoresis, magnetic separation, impingement filters, screen filters, fabric filters and scrubbers.

18. (Original) The method of claim 1, wherein the quenching is accomplished using adiabatic expansion.
19. (Original) The method of claim 1, wherein the method includes instrumentation for quality control.
20. (Original) The method of claim 1, wherein the process operates near ambient pressure.
21. (Withdrawn) The method of claim 1, wherein the process operates at a pressure less than 750 mm Hg absolute.
22. (Withdrawn) The method of claim 21, wherein the pressure is achieved using a compressed fluid-based eductor operating on a venturi principle.
23. (Withdrawn) A method of producing nanoscale particles in vacuum wherein the vacuum is achieved using a compressed fluid-based eductor operating on a venturi principle.
24. (Original) The method of claim 1, wherein the powder manufactured comprises nano-dispersed particles.
25. (Withdrawn) The method of claim 1, wherein the metal-containing precursor comprises nanoscale powder and coarse carrier particles.
26. (Withdrawn) The method of claim 1, wherein the powder manufactured comprises carrier particles comprising a ceramic and attached particles comprising a metal.
27. (Original) The method of claim 1, wherein the powder manufactured comprises carrier particles comprising a ceramic and attached particles comprising an alloy.
28. (Withdrawn) The method of claim 1, wherein the powder manufactured comprises carrier particles comprising a ceramic and attached particles comprising an oxide.
29. (Withdrawn) The method of claim 1, wherein the powder manufactured comprises carrier particles comprising a ceramic and attached particles comprising a ceramic.

PATENT

Attorney Docket No. 037768-0173

Application No. 10/698,564

30. (Withdrawn) A powder manufactured using the method of claim 1.
31. (New) The method of claim 1, wherein the metal-containing precursor is a metal carboxylate.
32. (New) The method of claim 1, further comprising harvesting the nucleated nanoscale powders.